



**Southeastern  
Felt & Supply Corp.**

## **SYNTHETIC FIBER FELTS – ROLL**

NOMEX®

### **General Properties**

Available Fiber Deniers, per filament	2 - 10
Available Densities	
1” Nominal Thickness, lbs/sq yd	4 - 18
Available Thickness Range, in.	1/16 – 1 1/2
Available Widths, in	up to 144

### **Chemical & Environmental Properties**

Temperature, degrees F, Max Service  
Condition under constant exposure 400

Effects of Acids & Alkalis Unaffected by most acids, except some strength loss after long exposure to hydrochloric, nitric, and sulfuric acids. Generally good resistance to alkalis.

Effects of Bleaches & Solvents Unaffected by most bleaches and solvents.

Resistance to Mildew, Aging, Sunlight  
and Abrasion Excellent resistance to mildew and aging. Prolonged exposure to sunlight causes some strength loss. Good abrasion resistance.

### **Typical Uses**

High temperature filter, gasket and wiper applications; fire-resistant apparel lining.

**Southeastern Felt & Supply Corp.**

**P.O. Box 1368**

**2870 Armentrout Drive**

**Concord, NC 28026**

**800 438-2252**

**704 782-7410 FAX**

**[info@sefelt.com](mailto:info@sefelt.com)**

**[www.sefelt.com](http://www.sefelt.com)**