



**Southeastern  
Felt & Supply Corp.**

## **SYNTHETIC FIBER FELTS – ROLL**

TEFLON®

### **General Properties**

Available Fiber Deniers, per filament	6.67
Available Densities	
1” Nominal Thickness, lbs/sq yd	4 - 18
Available Thickness Range, in.	1/16 – 1
Available Widths, in	72

### **Chemical & Environmental Properties**

Temperature, degrees F, Max Service Condition under constant exposure	550
Effects of Acids & Alkalis	Essentially inert to acids and alkalis.
Effects of Bleaches & Solvents	Most chemically-resistant fiber known. The only known solvents are alkali metals and certain perfluorinated organic liquids at temperatures above 570 degrees F.
Resistance to Mildew, Aging, Sunlight and abrasion	Not weakened by mildew. Excellent resistance to aging and sunlight. Good abrasion resistance.

### **Typical Uses**

High temperature filter, gasket and wiper applications; corrosive gasketing applications; dust bags requiring excellent particle release characteristics.

**Southeastern Felt & Supply Corp.**  
**P.O. Box 1368**  
**2870 Armentrout Drive**  
**Concord, NC 28026**

**800 438-2252**  
**704 782-7410 FAX**  
[info@sefelt.com](mailto:info@sefelt.com)  
[www.sefelt.com](http://www.sefelt.com)